

FORM PTO-1390
(REV. 11-2000)

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

0475-0201P

U.S. APPLICATION NO. (If known, see 37 CFR 1.5)

10/018660

INTERNATIONAL APPLICATION NO.

PCT/EP00/05737

INTERNATIONAL FILING DATE

June 21, 2000

PRIORITY DATE CLAIMED

June 21, 1999

TITLE OF INVENTION

POLYMERIZABLE DENTAL COMPOSITIONS

APPLICANT(S) FOR DO/EO/US

SOGOLOWEK, Wolfgang; O'CONNELL, Keith

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39 (1).
4. ☒ The US has been elected by the expiration of 19 months from the priority date (Article 31).
5. ☒ A copy of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. ☒ is transmitted herewith (required only if not transmitted by the International Bureau). WO 00/78271
 - b. ☒ has been transmitted by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).
 - a. ☒ is transmitted herewith.
 - b. ☐ has been previously submitted under 35 U.S.C. 154(d)(4)
7. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)).
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☐ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10. ☒ An English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11. to 20. below concern document(s) or information included:

11. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98, Form PTO-1449(s), and International Search Report (PCT/ISA/210) with 0 cited document(s).
12. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☒ A **FIRST** preliminary amendment.
14. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
15. ☐ A substitute specification.
16. ☐ A change of power of attorney and/or address letter.
17. ☐ A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821-1.825.
18. ☐ A second copy of the published international application under 35 U.S.C. 154(d)(4).
19. ☐ A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).
20. ☒ Other items or information:
 - 1.) PCT Substitute Claims Letter w/ PCT/IPEA/409 and amended claims (in German) and English Translation of Amended Claims
 - 2.) Zero (0) sheets of Formal Drawings

U.S. APPLICATION NO (if known, see 37 CFR 1.5) 10/018660		INTERNATIONAL APPLICATION NO PCT/EP00/05737		ATTORNEY'S DOCKET NUMBER 0475-0201P	
--	--	--	--	--	--

21. <input checked="" type="checkbox"/> The following fees are submitted: BASIC NATIONAL FEE (37 CFR 1.492(a)(1)-(5): Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO. \$1,040.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO \$890.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO. \$740.00 International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$710.00 International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4). \$100.00 ENTER APPROPRIATE BASIC FEE AMOUNT =	CALCULATIONS PTO USE ONLY																					
Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input checked="" type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(e)).	\$	890.00																				
<table border="1" style="width:100%; border-collapse: collapse;"> <tr> <th style="width:15%;">CLAIMS</th> <th style="width:25%;">NUMBER FILED</th> <th style="width:25%;">NUMBER EXTRA</th> <th style="width:35%;">RATE</th> </tr> <tr> <td>Total Claims</td> <td>12 - 20 =</td> <td>0</td> <td>X \$18.00</td> </tr> <tr> <td>Independent Claims</td> <td>1 - 3 =</td> <td>0</td> <td>X \$84.00</td> </tr> <tr> <td colspan="3">MULTIPLE DEPENDENT CLAIM(S) (if applicable) Yes</td> <td>+ \$280.00</td> </tr> <tr> <td colspan="3" style="text-align: right;">TOTAL OF ABOVE CALCULATIONS =</td> <td>\$ 1300.00</td> </tr> </table>	CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE	Total Claims	12 - 20 =	0	X \$18.00	Independent Claims	1 - 3 =	0	X \$84.00	MULTIPLE DEPENDENT CLAIM(S) (if applicable) Yes			+ \$280.00	TOTAL OF ABOVE CALCULATIONS =			\$ 1300.00	\$	130.00
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE																			
Total Claims	12 - 20 =	0	X \$18.00																			
Independent Claims	1 - 3 =	0	X \$84.00																			
MULTIPLE DEPENDENT CLAIM(S) (if applicable) Yes			+ \$280.00																			
TOTAL OF ABOVE CALCULATIONS =			\$ 1300.00																			
<input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above are reduced by 1/2.	\$	0																				
SUBTOTAL =	\$	1300.00																				
Processing fee of \$130.00 for furnishing the English translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(f)).	\$	0																				
TOTAL NATIONAL FEE =	\$	1300.00																				
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property +	\$	0																				
TOTAL FEES ENCLOSED =	\$	1300.00																				
Amount to be:		\$																				
refunded		\$																				
charged		\$																				

a. ☒ A check in the amount of \$ **1300.00** to cover the above fees is enclosed.


b. ☐ Please charge my Deposit Account. No. _____ in the amount of \$ _____ to cover the above fees.
 A duplicate copy of this sheet is enclosed.

c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 02-2448.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

Send all correspondence to:
Birch, Stewart, Kolasch & Birch, LLP or Customer No. 2292
 P.O. Box 747
 Falls Church, VA 22040-0747
 (703) 205-8000

Date: December 21, 2001

By 
 Andrew D. Meikle, #32,868

JC13 Rec'd PCT/PTO 21 DEC 2001

PATENT
0475-0201P

IN THE U.S. PATENT AND TRADEMARK OFFICE

Applicant: SOGOLOWEK, wolfgang et al.
Int'l. Appl. No.: PCT/EP00/05737
Appl. No.: New Group:
Filed: December 21, 2001 Examiner:
For: POLYMERIZABLE DENTAL COMPOSTIONS

PRELIMINARY AMENDMENT**BOX PATENT APPLICATION**

Assistant Commissioner for Patents
Washington, DC 20231

December 21, 2001

Sir:

The following Preliminary Amendments and Remarks are respectfully submitted in connection with the above-identified application.

AMENDMENTSIN THE TITLE:

Please amend the title to read:

--POLYMERIZABLE DENTAL COMPOSITIONS--

IN THE SPECIFICATION:

Please amend the specification as follows:

Before line 1, insert --This application is the national phase under 35 U.S.C. § 371 of PCT International Application No.

Docket No. 0475-0201P

PCT/EP00/05737 which has an International filing date of June 21,
2000, which designated the United States of America
and was published in English.--

REMARKS


The specification has been amended to provide a cross-reference to the previously filed International Application.

Entry of the above amendments is earnestly solicited. An early and favorable first action on the merits is earnestly solicited.

If necessary, the Commissioner is hereby authorized in this, concurrent, and future replies, to charge payment or credit any overpayment to Deposit Account No. 02-2448 for any additional fees required under 37 C.F.R. § 1.16 or under 37 C.F.R. § 1.17; particularly, extension of time fees.

Respectfully submitted,

BIRCH, STEWART, KOLASCH & BIRCH, LLP

By 
Andrew D. Meikle, #32,868

ADM/cqc
0475-0201P

P.O. Box 747
Falls Church, VA 22040-0747
(703) 205-8000

(Rev. 11/13/01)

Polymerisable dental compositions

The present invention relates to polymerisable dental compositions which contain

- a) 10 to 98.999 wt.-% of at least one bi- or higher-functional ethylenically unsaturated monomer,
- b) 0 to 88.999 wt.-% of at least one monofunctional ethylenically unsaturated monomer,
- c) 0 to 5 wt.-% of an accelerator,
- d) 0.001 to 5 wt.-% of a redox initiator system which can trigger the radical polymerisation,
- e) 0 to 88.999 wt.-% fillers, thixotropic auxiliaries, retarders and other auxiliaries and
- f) 1 to 30 wt.-% of a customary plasticizer.

Polymerisable dental compositions are suitable in particular as filling materials, stump build-up materials, fixing cements, temporary crown and bridge materials, dental materials, modelling materials or for the preparation of inlays, onlays, facing shells and temporary crowns and bridges.

Depending on the intended use, thinly liquid to viscoplastic compositions are involved which can be provided with organic or inorganic fillers, and cure during polymerisation.

Above all, ethylenically unsaturated compounds, such as acrylic acid and/or methylacrylic acid esters, are used as monomers of the polymerisable dental compositions.

The temporary crown and bridge materials are normally relatively low-filled systems which contain approx. 10 to 70 wt.-% inorganic filler. The fillers used have an average particle size of 1 to 15 μm . In addition however, much finer fillers in the range from 0.02 to 0.05 μm are also used with the above named fillers, in order to make the materials sufficiently plastic and thixotropic. The use of organic fillers, such as e.g. polymethyl methacrylate, has also proved successful.

When using these materials the monomers are mixed with suitable initiator systems shortly before being processed, a pasty composition forming which cures by radical polymerisation. The original components, which contain monomer and initiator systems among others, can also be present in the form of pastes spatially separated from each other or also as a powder-liquid system.

Various initiator systems are used to start the radical polymerisation. It is necessary that, after the polymerisation has started, the processing time until the material is cured is long enough to give the dentist enough time for the material to be matched and made available for processing. At the same time, however, the setting time from the beginning of gelling to an extensive curing of the material is also to be as short as possible, as working is not possible during this phase and the waiting time for the dentist and the patient should be as short as possible.

An initiator system already known for a long time consists of an amine and a peroxide component, such as described e.g. in patent specification DE-C-975 072. The polymerisation is started in this case by the peroxide compound. A tertiary amine is used for example to accelerate the polymerisation. Another such system is also described by Albert Groß in "Quintessenz der Zahntechnik", 1977, 7, Paper No. 293. There, secondary or tertiary amines accelerate the decomposition of the peroxide component, which triggers the polymerisation of the material. The amine component is normally introduced into a paste, the so-called base paste. This base paste also contains the monomers provided for polymerisation. The peroxide component is introduced into a further paste, the so-called catalyst paste. The spatial separation of the two initiator components is necessary in order to avoid a premature curing of the monomer portions. Also described in the German patent specification DE-C-955 633 is a similar initiator system for the polymerisation of unsaturated hydrocarbons which contains heavy metals as well as an amine and a sulphone component. An initiator system with an organic peroxide compound and a tertiary aromatic amine as activator (accelerator) is also named in the European patent specification EP-B-374 824.

A disadvantage of the materials named is that the amines suitable for a favourable setting phase tend to discolour. These yellow-brown discolorations are however not

acceptable in the dental field. In addition, tertiary aromatic amines can be used only under certain conditions due to their health risk. Furthermore, the increase in temperature during polymerisation of these systems, due to the exothermic reaction processes, causes problems. Too great a development of heat can lead to damage to the patient's pulp.

The initiator systems which are described in the German patent specification DE-C-14 95 520 have a more favourable temperature development and also better colour stability. The composition from DE-C-14 95 520 polymerises at low temperature in a short time and without using external energy. The systems described contain barbituric acid derivatives or malonyl sulfamides, organic peroxides, ionogenically bound halogen and/or a heavy metal compound. European patent specification EP-B-0 374 824 describes such an initiator system comprising barbituric acid derivative, peroxide, heavy metal compound and ionogenic halogen. Barbituric acid derivatives or malonyl sulfamides and peroxides cannot be stored together in these initiator systems. Furthermore, both named constituents of the initiator systems also have to be stored separately from the monomers. A storage in three pastes spatially separated from each other is necessary to provide polymerisable dental compositions which contain monomers, barbituric acid derivatives or malonyl sulfamides, organic peroxides, ionogenically bound halogen and/or a heavy metal compound.

This leads to a relatively costly handling of the systems. Three-component systems are not suitable for an automatic mixing. Therefore these conventional dental compositions comprising three components have to be mixed by hand, air being introduced and the dispensing of the individual components not being able to be so precise. The introduction of air is to be avoided above all because defects occur in the cured material, caused by introduced air bubbles. The fracture sensitivity increases and a poor surface condition results. Different dosages lead to changed setting times, poorer mechanical properties and an imprecise colouration. Furthermore, mixing by hand is more time-consuming than automatic mixing.

Alternatively, there is the possibility, as described e.g. in JP-A-02245080, to make barbituric acid derivatives and organic peroxides in the form of a powder available. Such powder-liquid systems are also described in DE-A-197 42 980 and US-A-

5,688,883. The peroxide component is contained in a solution, while the powder component has a barbituric acid derivative.

5 A two-component system with the named constituents is described in the German patent specification DE-C-37 25 502. This, however, is a powder-liquid system in which barbituric acid derivatives or malonyl sulfamides and peroxides are present as powder and there is adequate storage stability, because the two components do not react with each other to a noteworthy extent when in powdery state. The awkward handling is a disadvantage with such a powder-liquid system. For example, because of
10 the powder proportion, these systems cannot be used in mixing devices customary in the trade in dentistry, which are designed for paste-paste systems. In addition, more time is required for the mixing of a polymerisable dental composition comprising powder and liquid than for the mixing of pastes and there is the danger that air is introduced, with the above described disadvantages.

15 Two-component, automatically mixable paste-paste systems comprising the constituents which are listed in the named printed documents DE-C-37 25 502, DE-C-14 95 520 and EP-B-0 375 824, were hitherto unable to be prepared with sufficient storage stability.

20 It is thus the object of the present invention to make available a polymerisable dental composition, the initiator system of which contains (i) barbituric acid derivatives and/or malonyl sulfamides and (ii) organic peroxides as well as optionally ionogenic halogens and heavy metal compounds, the constituents of which can be present in two
25 components in the form of pastes spatially separated from each other, and which have a sufficient storage stability. As a rule, such compositions should be able to be stored for at least one year, in order to still have reasonable residual lives and use-by dates after being sold to the dentist.

30 This object is achieved by the provision of a dental composition which contains

- a) 10 to 98.999 wt.-% of at least one bi- or higher-functional ethylenically unsaturated monomer,
- b) 0 to 88.999 wt.-% of at least one monofunctional ethylenically unsaturated monomer,

- c) 0 to 5 wt.-% of an accelerator
- d) 0.001 to 5 wt.-% of a redox initiator system which can trigger the radical polymerisation,
- e) 0 to 88.999 wt.-% fillers, thixotropic auxiliaries, retarders and other auxiliaries and
- f) 1 to 30 wt.-% of a customary plasticizer

and is characterized in that the redox initiator system comprises (i) a barbituric acid derivative and/or a malonyl sulfamide and (ii) an organic peroxide, selected from the group of the mono- or multifunctional carboxylic acid peroxyesters, and the constituents (a) to (f) are present in two pastes spatially separated from each other.

Surprisingly, it was found that, because of the special use of an organic peroxide from the group of the mono- or multifunctional carboxylic acid peroxyesters, the constituents of the polymerisable dental composition (a) to (f) can be present in two pastes spatially separated from each other. In the case of the preparations known from the state of the art, such an administration was not possible since, as already described above, in that component which at the same time contained (i) a barbituric acid derivative and/or a malonyl sulfamide and (ii) a customary organic peroxide, these two components reacted with each other within a short storage period and, as a result, a setting no longer occurred within a reasonable period of time after the addition of the monomer-containing component.

When using the organic peroxides according to the invention, it has been found, contrary to expectation, that a component which at the same time contains (i) a barbituric acid derivative and/or a malonyl sulfamide and (ii) an organic peroxide has an adequate storage stability, so that a provision in the form of two pastes spatially separated from each other becomes possible.

The two pastes spatially separated from each other can be prepared as base and catalyst pastes, the base paste containing the constituents (a), (b) and (c) and the catalyst paste the constituents (d) and (f). Furthermore the base paste can additionally contain the constituents (e) and/or (f), the catalyst paste additionally the constituent (e).

By the term "monofunctional" or "bi- or higher-functional ethylenically unsaturated monomers", within the meaning of the present invention, are meant polymerisable compounds which have an oligomeric or polymeric basic structure and carry at least one ethylenically unsaturated group. This ethylenically unsaturated group can be present for example as an acrylate and/or methacrylate group which is covalently bound to the basic structure. The polymeric basic structure can be e.g. a polyethylene oxide, a polyester, a polyurethane, a polycarbonate, a polyalcohol, a polystyrene or a polymerisable ethylenically unsaturated compound.

Methacrylate and acrylate monomers, such as e.g. methyl(meth)acrylate, n- or i-propyl(meth)acrylate, n-, i- or tert.butyl(meth)acrylate and 2-hydroxyl(meth)acrylate, 2-(meth)acryloxy-tetrahydrofuran, 2-(((alkylamino)-carbonyl)-oxy)ethyl-(meth)acrylates; di(meth)acrylates of propanediol, butanediol, hexanediol, octanediol, nonanediol, decanediol and eicosanediol; di(meth)acrylates of ethylene glycol, polyethylene glycols, polypropylene glycols; di(meth)acrylates of ethoxylated bisphenol A, e.g. 2,2'-bis(4-(meth)acryloxy-tetraethoxyphenyl)propane; urethane(meth)acrylates; (meth)acryl-amides are particularly preferred as monofunctional or bi- or higher-functional ethylenically unsaturated monomers of constituent (a) or (b).

Furthermore, esters of α -cyanoacrylic acid, crotonic acid, cinnamic acid, sorbic acid, vinyl ethers, such as e.g. butyl vinyl ether; mono-N-vinyl- compounds, such as N-vinyl pyrrolidone, can be used as monomers of the constituents (a) and (b).

Furthermore, the methylacrylic acid esters named in the European patent application EP-A-0 235 826, such as e.g. triglycolic acid-bis[3[4]-methacryloxymethyl-8(9)-tricyclo-[5.2.1.0^{2,6}]-decyl methyl ester, can be used.

Suitable in particular are 2,2-bis-4(3-methacryloxy-2-hydroxypropoxy)phenylpropane (bis-GMA), 2,2-bis-4(3-methacryloxy-propoxy)phenylpropane, triethylene glycol dimethacrylate (TEGDMA), 7,7,9-trimethyl-4,13-dioxo-3,14,-dioxo-5,12-diazahexadecane-1,16-dioxy-dimethacrylate (UDMA) and di(meth)acrylates of bishydroxymethyltricyclo(5.2.1.0^{2,6})-decane.

These ethylenically unsaturated monomers can be used in the disclosed dental compositions either alone or in combination with further ethylenically unsaturated monomers.

According to the invention, the bi- or higher-functional ethylenically unsaturated monomers are used in a concentration of 10 to 98.999 wt.-%, preferably from 30 to 80 wt.-%, in each case relative to the total mass of the constituents (a) to (f). A use of 45 to 70 wt.-% of constituent (a) in the polymerisable dental composition is particularly preferred.

Constituent (b) is used in a concentration of 0 to 88.999 wt.-% relative to the total mass of constituents (a) to (f). A concentration of monofunctional ethylenically unsaturated monomers according to component (b) of 0 to 58.99 wt.-%, preferably from 0 to 33.99 wt.-% is suitable in particular.

Heavy metal compounds, in particular metals of the iron or the copper groups, preferably copper are suitable as accelerator according to constituent (c). The heavy metal is suitably used in the form of soluble organic compounds. In addition, there can be added as accelerators ionogenically bound halogens or pseudohalogens, e.g. Cl^- -containing compounds, preferably in the form of soluble salts, in particular organic ammonium chlorides or hydrochlorides. These compounds are contained in the polymerisable dental composition in a concentration of 0 to 5 wt.-%, preferably from 0 to 3 wt.-%, particularly preferably from 0.05 to 2 wt.-%. A mixture of several accelerators can also be used.

Furthermore, the polymerisable dental composition according to the invention can contain as constituent (e) 0 to 88.999 wt.-%, in particular 10 to 68.99 wt.-% and particularly preferably 20 to 53.9 wt.-% customary fillers for dental materials, such as for example glass and quartz powders, silica gels, pyrogenic highly-dispersed silicic acids or low soluble fluorides as well as mixtures of these components. These fillers can be x-ray opaque through suitable additives, such as for example barium- or strontium-containing glasses. For example, pyrogenic highly-dispersed silicic acids are suitable as thixotropic auxiliaries. Further auxiliaries are for example dyes,

pigments, flow-improvers, polymeric thickening agents or stabilizers. To increase the flexibility of the dental composition, soluble organic polymerisates such as e.g. polyvinyl acetate as well as its copolymers, can also be added.

5 Christobalite, calcium silicate, zirconium silicate, montmorillonites, such as bentonites, zeolites, including molecular sieves, such as sodium aluminium silicate, metallic oxide powders, such as aluminium or zinc oxides or their mixed oxides, barium sulphate, yttrium fluoride, calcium carbonate, gypsum and synthetic powders are also suitable as fillers for the dental composition according to the invention.

10

The named fillers can also be hydrophobized by e.g. a treatment with organosilanes or -siloxanes or by the etherification of hydroxyl groups to alkoxy groups.

15

The compounds described in European patent specification EP-B-0 374 824 are suitable as retarders.

20

The redox initiator system to be used according to the invention consists of (i) a barbituric acid derivative and/or a malonyl sulfamide and (ii) an organic peroxide, selected from the group of the mono- or multifunctional carboxylic acid peroxide esters. There can be used as barbituric acid derivatives, for example, 1,3,5-trimethylbarbituric acid, 1,3,5-triethylbarbituric acid, 1,3-dimethyl-5-ethylbarbituric acid, 1,5-dimethylbarbituric acid, 1-methyl-5-ethylbarbituric acid, 1-methyl-5-propylbarbituric acid, 5-ethylbarbituric acid, 5-propylbarbituric acid, 5-butylbarbituric acid, 1-benzyl-5-phenylbarbituric acid, 1-cyclohexyl-5-ethylbarbituric acid and the

25

thiobarbituric acids mentioned in the German patent application DE-A-42 19 700.

The barbituric acids and barbituric acid derivatives described in German patent specification DE-C-14 95 520 as well as the malonyl sulfamides named in the European patent specification EP-B-0 059 451 are well suited. Preferred malonyl

30

sulfamides are 2,6-dimethyl-4-isobutylmalonyl sulfamide, 2,6-diisobutyl-4-propylmalonyl sulfamide, 2,6-dibutyl-4-propylmalonyl sulfamide, 2,6-dimethyl-4-ethylmalonyl sulfamide or 2,6-dioctyl-4-isobutylmalonyl sulfamide.

The redox initiator system according to the invention contains mono- or multifunctional carboxylic acid peroxyesters as organic peroxides. Carbonic peroxyesters are also included among the multifunctional carboxylic acid peroxyesters within the meaning of the present application.

5

Suitable are for example carbonic-diisopropyl-peroxydiester, neodecanoic acid-tertiarybutyl-peroxyester, neodecanoic acid-tertiaryamyl-peroxyester, maleic acid-tertiarybutyl-monoperoxyester, benzoic acid-tertiarybutyl-peroxyester, 2-ethylhexanoic acid-tertiarybutyl-peroxyester, 2-ethylhexanoic acid-tertiaryamyl-peroxyester, carbonic-monoisopropylester-monotertiarybutyl-peroxyester, carbonic-dicyclohexyl-peroxyester, carbonic-dimyristyl-peroxyester, carbonic dicetyl-peroxyester, carbonic-di(2-ethylhexyl)-peroxyester, carbonic-tertiarybutyl-peroxy-(2-ethylhexyl)ester or 3,5,5-trimethylhexanoic acid-tertiarybutyl-peroxyester, benzoic acid-tertiaryamyl-peroxyester, acetic acid-tertiarybutyl-peroxyester, carbonic-di(4-tertiarybutyl-cyclohexyl)-peroxyester, neodecanoic acid-cumene-peroxyester, pivalic acid-tertiaryamyl-peroxyester and pivalic acid tertiarybutyl-peroxyester.

10

15

20

In particular, carbonic-tertiarybutyl-peroxy-(2-ethylhexyl)ester or 3,5,5-trimethylhexanoic acid-tertiarybutyl-peroxyester can be used as organic peroxides according to the invention.

The dental compositions according to the invention contain the redox initiator system in a concentration of 0.001 to 5 wt.-%, preferably in a concentration of 0.01 to 3 wt.-%, relative to the total mass of the constituents (a) to (f). An initiator system concentration of 0.05 to 2 wt.-% is particularly preferred.

25

As constituent (f) the polymerisable dental composition according to the invention contains 1 to 30 wt.-%, preferably 1 to 20 wt.-%, in particular 1 to 15 wt.-%, of a customary plasticizer or a mixture of customary plasticizers. These are for example polyethylene glycol derivatives, polypropylene glycols, low-molecular-weight polyesters, dibutyl-, dioctyl-, dinonyl-, diphenylphthalate, di(iso-nonyladipate), tricresylphosphate and silicone oils.

30

For the following examples the dental compositions according to the invention were prepared as two-component paste systems in the form of base and catalyst pastes. The base paste contained the constituents (a), (b), (c) and (e) in the amounts in wt.-% that can be seen from Table 1. Constituent (f) can alternatively also be added. The catalyst

5 paste contained the constituents (d), (e) and (f), the inclusion of (e) not being obligatory. To prepare the two pastes, the respective constituents of the base and catalyst pastes were kneaded to homogenous pastes with a 3-arm kneader under vacuum.

- 10 The catalyst pastes 1, 2 and 3 contained customary peroxides known from the state of the art. These pastes served to prepare comparative tests. The catalyst pastes 4 and 5 included the peroxides according to the invention.

For the following tests a mixture ratio of base-to-catalyst paste of 10:1 was selected.

- 15 Naturally, the two-component systems according to the invention can also be prepared with other mixture ratios.

Table 1

BASE PASTE	glass powder	34 wt.-%
	microfine silicic acid	8 wt.-%
	bis-(1-phenylpentane-1,3-dionato)-copper(II)	0.0013 wt.-%
	(β -phenylethyl)-dibutyl-ammonium-chloride	0.36 wt.-%
	2,2-bis-{4-[oligo(ethoxy))phenyl}-propane-dimethacrylate	made up 100 wt.-%
CATALYST PASTE 1	glass powder	34 wt.-%
	microfine silicic acid	8 wt.-%
	1-benzyl-5-phenylbarbituric acid	0.6 wt.-%
	2,2-bis-4-(2-hydroxyethoxyphenyl)-propane-bis-acetate	made up 100 wt.-%
	dibenzoyl peroxide	3.9 wt.-%
CATALYST PASTE 2	glass powder	34 wt.-%
	microfine silicic acid	8 wt.-%
	1-benzyl-5-phenylbarbituric acid	0.6 wt.-%
	2,2-bis-4-(2-hydroxyethoxyphenyl)-propane-bis-acetate	made up 100 wt.-%
	dilauroyl peroxide	8.0 wt.-%
CATALYST PASTE 3	glass powder	34 wt.-%
	microfine silicic acid	8 wt.-%
	1-benzyl-5-phenylbarbituric acid	0.3 wt.-%
	2,2-bis-4-(2-hydroxyethoxyphenyl)-propane-bis-acetate	made up 100 wt.-%
	cumene hydroperoxide	0.48wt.-%
CATALYST PASTE 4	glass powder	34 wt.-%
	microfine silicic acid	8 wt.-%
	1-benzyl-5-phenylbarbituric acid	0.6 wt.-%
	2,2-bis-4-(2-hydroxyethoxyphenyl)-propane-bis-acetate	made up 100 wt.-%
	carbonic-tertiarybutylperoxy-(2-ethylhexyl)ester	0.6 wt.-%
CATALYST PASTE 5	glass powder	34 wt.-%
	microfine silicic acid	8 wt.-%
	1-benzyl-5-phenylbarbituric acid	0.6 wt.-%
	2,2-bis-4-(2-hydroxyethoxyphenyl)-propane-bis-acetate	made up 100 wt.-%
	3,5,5-trimethylhexanoic acid-tertiarybutylperoxyester	0.6 wt.-%

The various catalyst pastes of the dental compositions according to the invention were stored for extended periods and the setting times of the dental compositions mixed from the two components were measured at various storage times.

5

The setting times were measured after a maximum of 3 days' storage at room temperature. This value is shown in Table 2 as starting value. The catalyst paste was then stored in a heating cabinet at 50°C and the setting time checked after the stated time intervals (see Table 2). The base paste was stored at room temperature. The hot storage at 50°C is a generally recognised test under stress conditions which, on the basis of the results which are obtained at increased temperatures, permits conclusions to be drawn about the stability during storage under normal temperatures. These temperatures are however also completely realistic, as the dental compositions described can be subjected to such temperatures during transportation.

10
15

The setting times were measured as follows:

The base paste (1.00 g) and the corresponding catalyst pastes 1 – 5 (0.10 g) were weighed in on a mixing block and homogenously mixed. The setting time of the mixed paste was measured using a curometer (Wallace-Shawbury, England).

20

The results of the setting times measured are shown in Table 2, the expression >20 mins meaning that complete setting was not observed within 20 mins and therefore the test in question was terminated.

Table 2

	Start	1 day (50°C)	3 days (50°C)	1 week (50°C)	2 weeks (50°C)	3 weeks (50°C)
CATALYST PASTE 1						
setting time [min'sec]	2'55	>20'00	>20'00	>20'00	>20'00	>20'00
CATALYST PASTE 2						
setting time [min'sec]	2'35		>20'00	>20'00	>20'00	>20'00
CATALYST PASTE 3						
setting time [min'sec]	3'45		>20'00	>20'00	>20'00	>20'00
CATALYST PASTE 4						
setting time [min'sec]	2'00	2'00	2'05	2'25	2'25	2'35
CATALYST PASTE 5						
setting time [min'sec]	2'05	2'00	1'55	1'55	2'00	2'10

Patent claims

1. Polymerisable dental composition, containing

- 5 (a) 10 to 98.999 wt.-% of at least one bi- or higher-functional ethylenically unsaturated monomer,
- (b) 0 to 88.999 wt.-% of at least one monofunctional ethylenically unsaturated monomer,
- (c) 0 to 5 wt.-% of an accelerator,
- 10 (d) 0.001 to 5 wt.-% of a redox initiator system which can trigger the radical polymerisation, and
- (e) 0 to 88.999 wt.-% fillers, thixotropic auxiliaries, retarders and other auxiliaries,
- (f) 1 to 30 wt.-% of a customary plasticizer

15 characterized in that the redox initiator system comprises (i) a barbituric acid derivative and/or a malonyl sulfamide and (ii) an organic peroxide, selected from the group of the mono- or multifunctional carboxylic acid peroxyesters, and the constituents (a) to (f) are present in two pastes spatially separated from each other.

- 20 2. Polymerisable dental composition according to claim 1, characterized in that one of the two pastes separated spatially from each other includes (i) a barbituric acid derivative and/or a malonyl sulfamide and (ii) an organic peroxide, selected from the group of the mono- or multifunctional
- 25 carboxylic acid peroxyesters.

3. Polymerisable dental composition according to one of claims 1 or 2, characterized in that the organic peroxide is a carboxylic acid tertiarybutyl-peroxyester.

- 30 4. Polymerisable dental composition according to one of claims 1 to 3, characterized in that the organic peroxide is a carbonic-tertiarybutyl-peroxy-(2-ethylhexyl)ester or a 3,5,5-trimethylhexanoic acid-tertiarybutyl-peroxyester.

5. Polymerisable dental composition according to one of the previous claims, characterized in that constituent (a) is contained in a concentration of 30 to 80 wt.-%, preferably in a concentration of 45 to 70 wt.-%.
- 5 6. Polymerisable dental composition according to one of the previous claims, characterized in that constituent (b) is contained in a concentration of 0 to 58.99 wt.-%, in particular in a concentration of 0 to 33.9 wt.-%.
- 10 7. Polymerisable dental composition according to one of the previous claims, characterized in that constituent (c) is contained in a concentration of 0 to 3 wt.-%, in particular in a concentration of 0.05 to 2 wt.-%.
- 15 8. Polymerisable dental composition according to one of the previous claims, characterized in that constituent (d) is contained in a concentration of 0.01 to 3 wt.-%, preferably in a concentration of 0.05 to 2 wt.-%.
- 20 9. Polymerisable dental composition according to one of the previous claims, characterized in that constituent (e) is contained in a concentration of 10 to 68.99 wt.-%, preferably in a concentration of 20 to 53.9 wt.-%.
10. Polymerisable dental composition according to one of the previous claims, characterized in that constituent (f) is contained in a concentration of 1 to 20 wt.-%, preferably in a concentration of 1 to 15 wt.-%.
- 25 11. Use of the polymerisable dental composition according to claims 1 to 10 as filling material, stump build-up material, fixing cement, temporary crown and bridge material, dental material or for the preparation of inlays, onlays, facing shells, modelling materials.

Abstract

The invention relates to polymerisable dental compositions which contain

- (a) 10 to 98.999 wt.-% of at least one bi- or higher-functional ethylenically unsaturated monomer,
- (b) 0 to 88.999 wt.-% of at least one monofunctional ethylenically unsaturated monomer,
- (c) 0 to 5 wt.-% of an accelerator,
- (d) 0.001 to 5 wt.-% of a redox initiator system which can trigger the radical polymerisation and
- (e) 0 to 88.999 wt.-% fillers, thixotropic auxiliaries, retarders and other auxiliaries
- (f) 1 to 30 wt.-% of a customary plasticizer

and are characterized in that the redox initiator system comprises (i) a barbituric acid derivative and/or a malonyl sulfamide and (ii) an organic peroxide, selected from the group of the mono- or multifunctional carboxylic acid peroxyesters, and the constituents (a) to (f) are present in two pastes spatially separated from each other. The dental compositions are suitable as filling material, stump build-up material, fixing cement, temporary crown and bridge material, dental material or for the preparation of inlays, onlays, facing shells, modelling materials.

BIRCH, STEWART, KOLASCH & BIRCH, LLPP.O. Box 747 - Falls Church, Virginia 22040-0747
Telephone: (703) 205-8000 - Facsimile: (703) 205-8050PLEASE NOTE:
YOU MUST
COMPLETE THE
FOLLOWING**COMBINED DECLARATION AND POWER OF ATTORNEY
FOR PATENT AND DESIGN APPLICATIONS**

As a below named inventor, I hereby declare that: my residence, post office address and citizenship are as stated next to my name; that I verily believe that I am the original, first and sole inventor (if only one inventor is named below) or an original, first and joint inventor (if plural inventors are named below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

POLYMERISABLE DENTAL COMPOSITIONS

the specification of which is attached hereto. If not attached hereto,

the specification was filed on _____ as
United States Application Number _____
and amended on _____ (if applicable) and/or
the specification was filed on June 21, 2000 as PCT
International Application Number PCT/EP00/05737 ; and was
amended on September 7, 2001 (if applicable)

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, §1.56. I do not know and do not believe the same was ever known or used in the United States of America before my or our invention thereof, or patented or described in any printed publication in any country before my or our invention thereof or more than one year prior to this application, that the same was not in public use or on sale in the United States of America more than one year prior to this application, that the invention has not been patented or made the subject of an inventor's certificate issued before the date of this application in any country foreign to the United States of America on an application filed by me or my legal representative or assigns more than twelve months (six months for designs) prior to this application, and that no application for patent or inventor's certificate on this invention has been filed in any country foreign to the United States of America prior to this application by me or my legal representatives or assigns, except as follows:

I hereby claim foreign priority benefits under Title 35, United States Code, §119(a)-(d) of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed.

Prior Foreign Application(s)**Priority Claimed**

<u>199 28 238.2</u> (Number)	<u>Germany</u> (Country)	<u>June 21, 1999</u> (Month/Day/Year Filed)	<input checked="" type="checkbox"/> Yes	<input type="checkbox"/> No
_____ (Number)	_____ (Country)	_____ (Month/Day/Year Filed)	<input type="checkbox"/> Yes	<input type="checkbox"/> No
_____ (Number)	_____ (Country)	_____ (Month/Day/Year Filed)	<input type="checkbox"/> Yes	<input type="checkbox"/> No
_____ (Number)	_____ (Country)	_____ (Month/Day/Year Filed)	<input type="checkbox"/> Yes	<input type="checkbox"/> No

I hereby claim the benefit under Title 35, United States Code, §119(c) of any United States provisional application(s) listed below.

_____ (Application Number)	_____ (Filing Date)
_____ (Application Number)	_____ (Filing Date)

All Foreign Applications, if any, for any Patent or Inventor's Certificate Filed More than 12 Months (6 Months for Designs) Prior to the Filing Date of This Application:

Country	Application Number	Date of Filing (Month/Day/Year)
_____	_____	_____
_____	_____	_____

I hereby claim the benefit under Title 35, United States Code, §120 of any United States and/or PCT application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States and/or PCT application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose information which is material to the patentability as defined in Title 37, Code of Federal Regulations, §1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application.

_____ (Application Number)	_____ (Filing Date)	_____ (Status - patented, pending, abandoned)
_____ (Application Number)	_____ (Filing Date)	_____ (Status - patented, pending, abandoned)

Insert Title
Page in Appropriate
Information -
For Use Without
Specification
AttachedInsert Priority
Information
(If Applicable)Insert Provisional
Application(s)Insert Requested
Information
(If Applicable)Insert Prior U.S.
Application(s)
(if any)Form 1002
(Rev. 12/1997)

I hereby appoint the practitioners at CUSTOMER NO. 2292 as my attorneys or agents to prosecute this application and/or an international application based on this application and to transact all business in the United States Patent and Trademark Office connected therewith and in connection with the resulting patent based on instructions received from the entity who first sent the application papers to the practitioners, unless the inventor(s) or assignee provides said practitioners with a written notice to the contrary.

Send Correspondence to:

BIRCH, STEWART, KOLASCH & BIRCH, LLP or **CUSTOMER NO. 2292**
P.O. Box 747 • Falls Church, Virginia 22040-0747
Telephone: (703) 205-8000 • Facsimile: (703) 205-8050

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

GIVEN NAME/FAMILY NAME Wolfgang SOGLOWEK		INVENTOR'S SIGNATURE <i>Wolfgang Soelowek</i>	DATE* 21 Feb 2002
Residence (City, State & Country) Diessen-Obermühlhausen GERMANY		CITIZENSHIP German	
MAILING ADDRESS (Complete Street Address including City, State & Country) Bergstrasse 30, D-86911 Diessen-Obermühlhausen GERMANY			
GIVEN NAME/FAMILY NAME Keith O'CONNELL		INVENTOR'S SIGNATURE <i>Keith O'Connell</i>	DATE* 18 FEB 2002
Residence (City, State & Country) Maidenhead, United Kingdom		CITIZENSHIP German IRISH	
MAILING ADDRESS (Complete Street Address including City, State & Country) 8 Castle Lodge, Frascati Way, Maidenhead, Berkshire, SL6 4UZ, United Kingdom			
GIVEN NAME/FAMILY NAME		INVENTOR'S SIGNATURE	DATE*
Residence (City, State & Country)		CITIZENSHIP German	
MAILING ADDRESS (Complete Street Address including City, State & Country)			
GIVEN NAME/FAMILY NAME		INVENTOR'S SIGNATURE	DATE*
Residence (City, State & Country)		CITIZENSHIP	
MAILING ADDRESS (Complete Street Address including City, State & Country)			
GIVEN NAME/FAMILY NAME		INVENTOR'S SIGNATURE	DATE*
Residence (City, State & Country)		CITIZENSHIP	
MAILING ADDRESS (Complete Street Address including City, State & Country)			
GIVEN NAME/FAMILY NAME		INVENTOR'S SIGNATURE	DATE*
Residence (City, State & Country)		CITIZENSHIP	
MAILING ADDRESS (Complete Street Address including City, State & Country)			

*DATE OF SIGNATURE